

#### PRODUCT DESCRIPTION

weber.color power is anti-fungus and anti-dirt tile grout with good bonding ideal for grouting floors and walls in bathrooms and kitchens.

• PACKAGING: 1 kg bag

COLOR: 40 colors

PO-111	snow	PO-112	steel	PO-113	ivory	PO-114	iron	PO-115	granite	PO-116	charcoal	PO-121	light
PO-122	pear	PO-123	moon	PO-124	lemon	PO-125	orange	PO-126	vanilla	PO-127	metalic	PO-128	mefil
PO-131	sky	PO-132	sea	PO-133	marine	PO-134	ocean	PO-135	pacific	PO-136	fresh	PO-141	coral
PO-142	rose	PO-143	orchid	PO-144	amethyst	PO-145	ruby	PO-146	pearl	PO-151	puddy	PO-152	earth
PO-153	wood	PO-154	stone	PO-155	rock	PO-156	pottery	PO-157	sand	PO-161	farm	PO-162	tree
PO-163	field	PO-164	leaf	PO-165	emerald	PO-166	mint	PO-167	herb				

\*These color presentations are as close as printing techniques permit. It is recommended to use the actual grout presenter for final selection.

• COVERAGE: average 5 m²/1 kg bag

# APPLICATION

# Substrate preparation

- Properly clean the joints until free from any dirt to make sure of good bonding and color uniformity

### Mixing

- Put clean water in mixing bucket
- Gradually add weber.color power into the water with the ratio of 1:2.5 by volume (1 part of water + 2.5 part of the grout) and mix until obtaining homogeneous lump-free paste
- Leave the mixture for 3 4 minutes for chemical curing
- The mixture of **weber.color power** can be used within 30 minutes after mixing when placing in shade

### Grouting

- Use rubber trowel or grout trowel to diagonally fill up the joints.
- Wipe off excess grout with damp sponge before the grout sets.
- Leave for 2 hours and then clean tiles' surface with clean cloth
- Wait for 24 hours before traffic to ensure good bonding of the grout

### SHELF LIFE AND STORAGE

One year after manufacturing date when stored unopened in dry and ventilated place. Store airtight in dry and ventilated conditions if remained in opened bag

### TECHNICAL DATA

Туре	Cementitious grout
Density of powder	0.9 – 1.1 g/cm <sup>3</sup>
Chemical curing time	3 – 4 minutes
Pot life (in shade)	30 minutes
Waiting time after tiling before grouting	24 hours
Recommended joint width	1 – 6 mm
Time before traffic	24 hours

Remark: These test results are from laboratory test. They could be slightly different from on-site results because of the differences in applications and conditions

# **CERTIFIED STANDARD**

International/European standard	Standard	Result
Abrasion resistance ISO 13007 part 4.4.4 or EN 12808-2	≤ 2,000 mm³	361 mm <sup>3</sup>
Flexural strength under standard condition ISO 13007 part 4-4.1.3 or EN 12808-3	≥ 2.5 N/mm²	4.15 N/mm²
Compressive strength under standard condition ISO 13007 part 4-4.1.4 or EN 12808-3	≥ 15.0 N/mm²	16.81 N/mm²
Shrinkage ISO 13007 part 4-4.3 or EN 12808-4	≤ 3.0 mm/m	2.24 mm/m
Water absorption after 30 minutes ISO 13007 part 4-4.2 or EN 12808-5	≤ 5.0 g	2.30 g
Water absorption after 240 minutes ISO 13007 part 4-4.2 or EN 12808-5	≤10 g	5.90 g

