








Dustless: excellence for renovation works





Laying tiles direct on lightweight block without render



Laying tiles on internal existing tiles



Cost saving with 35% more coverage



Low VOCs

PRODUCT DESCRIPTION

weber.tai maxx is dustless and lightweight high performance tile adhesive mixing with water providing excellent bonding. Ideal for tiling of renovation project, laying tiles on internal existing tiles, and laying tiles on lightweight blocks without render.

• SUITABLE FOR: ceramic tiles, granito tiles, marbles, granites, artificial tiles size up to 1 x 1 m

PACKAGING: 15 kg bag

COLOR: grey

• COVERAGE average 4 m²/15 kg bag

APPLICATION

Substrate preparation

- New substrate should be sound, level, and clean with normal absorption rate
- Case of existing substrate; check bonding. Remove peel-off paint and de-bonded tiles and lay the new ones. Clean off any excess dirt and laitance.
- In case of porous substrate with high absorption, dampen the surface before
- For new render or screed, it should be fully cured at the rate of 7 days per 1 cm thickness before tiling

Mixing weber.tai maxx in water with the ratio of 1:2.5 by volume (1 part of water + 2.5 parts of weber.tai maxx). Using slow-speed electric mixer to mix or gradually mix by hand until obtaining homogeneous lump-free paste. Leave for 3 - 4 minutes for chemical curing before using.

- 1. Using notched trowel to spread tile adhesive onto substrate
- 2. Back buttering in case of laying tile bigger than 10 x 10 inches
- 3. Placing tiles on tile adhesive and knock gradually with rubber hammer
- 4. Clean the excess tile adhesive on tile surface
- 5. Tiles can be adjusted within 15 minutes after laying
- 6. Leave for 24 hours before grouting

SHELF LIFE AND STORAGE

One year after manufacturing date when stored unopened in dry and ventilated place. Store airtight in dry and ventilated conditions if remained in opened bag

TECHNICAL DATA

Туре	High performance tile adhesive	
Density of powder	1.0 g/cm ³	
Chemical curing time	3 – 4 minutes	
Pot life (in shade)	4 hours	
Open time	20-30 minutes	
Adjusting time	15 minutes	
Recommended thickness	2 – 10 mm	
Waiting time before grouting	24 hours	

Remark: These test results are from laboratory test. They could be slightly different from on-site results because of the differences in applications and conditions

CERTIFIED STANDARD

International/European standard	Standard	Result
Initial tensile adhesion strength ISO 13007 part 2-4.4.4.2 or EN 1348-8.2	≥1.0 N/mm²	1.50 N/mm²
Tensile adhesion strength after water immersion ISO 13007 part 2-4.4.4.3 or EN 1348-8.3	≥1.0 N/mm²	1.20 N/mm²

