



webertai green

Tile adhesive for ceramic and granito tiles on cement floor



Laying ceramic and granito tiles size up to 60x60 cm.



Save time and fast installation



Easy to use, can provide 5-15 mm. thickness

• PRODUCT DESCRIPTION

webertai green cementitious pre-mixed tile adhesive to mix with water and lay ceramic and granito tiles on floors

- SUITABLE FOR : ceramic tiles, clay tiles and granito tiles
- PACKAGING : 20 kg bag
- COLOR : grey
- COVERAGE : average 3 m²/ 20 kg bag (5 mm. thickness)

• အသုံးပြုပုံအဆင့်ဆင့်

မျက်နှာပြင် ပြင်ဆင်ခြင်း

- မျက်နှာပြင်သည် မာကျော ညီညာ သန့်ရှင်းပြီး သာမန်ရေစုပ်နှုန်းရှိရမည်။

- i us substrate with high absor ti ,

. မျက်နှာပြင်အား သဲ၊ဖုန်မှုန့်၊ချောဆီ နှင့် အခြားသောအညစ်အကြေးတို့မှ ကင်း

- For new render or screed, it should be fully cured at rate of 7 days per 1 cm thickness before tiling

ရောစပ်ပုံ

Mixing **webertai green** in water with the ratio of 1:3 by volume (1 part of water + 3 parts **webertai green**). Using slow-speed electric mixer to mix or gradually mix by hand until obtaining homogeneous lump-free paste. Leave for 3-4 minutes for chemical curing before using.

ကြွေပြားကပ်ခြင်း

1. Using notched trowel to spread tile adhesive onto sub
2. Back buttering in case of laying tile bigger than 10 x 10 i
3. Placing tiles on tile adhesive and knock gradually with rubber hammer
4. Clean the excess tile adhesive on tile surface
5. Tiles can be adjusted within 5 minutes after laying
6. Leave for 24 hours before grouting



• SHELF LIFE AND STORAGE

One year after manufacturing date when stored unopened in dry and ventilated place. Store airtight in dry and ventilated conditions if remained in opened bag

TECHNICAL DATA

Type	Normal tile adhesive
Density of powder	1.4 g/cm ³
Chemical curing time	3-4 minutes
Pot life (in shade)	2 hours
Open time	15 minutes
Adjusting time	5 minutes
Recommended thickness	5-15 mm
Waiting time before grouting	24 hours

Remark : These test results are from laboratory test. They could be slightly different from on-site results because of the differences in applications and conditions

CERTIFIED STANDARD

International / European standard	Standard	Result
Initial tensile adhesion strength ISO 13007 part 2-4.4.4.2 or (EN 1348-8.2)	≥0.5 N/mm ²	0.84 N/mm ²
Tensile adhesion strength after water immersion ISO 13007 part 2-4.4.4.3 or (EN 1348-8.3)	≥0.5 N/mm ²	0.90 N/mm ²
Open time tensile adhesion strength ISO 13007 part 2-4.1 or (EN 1346)	≥0.5 N/mm ²	0.61 N/mm ²