



Type	ready-to-use skim coat
Density	1.6
pH	9
Composition	Synthetic resin, filler and admixture
Bonding strength	>0.5 N/mm <sup>2</sup>
Application temperature	5-35 °C
Waiting time before sandpaper over the dry final surface	12-24 hour
Waiting time before painting	1-2 day